

**Test Report** No.: CZHL2303001754HI **Date**: APR. 06, 2023 Page 1 of 3

GUANGZHOU HEDSOM BUILDING MATERIAL CO.,LTD

ROOM 221, NO.10 HUICAI ROAD, TIANHE DISTRICT, GUANGZHOU,510660,CHINA

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Sample Description : CONDUCTIVE PVC FLOOR TILE

Style No. : HP

\*\*\*\*\*

Sample Receiving Date : MAR. 29, 2023

Testing Period : MAR. 29, 2023 TO APR. 06, 2023

Testing Performed : Follow selected test(s) as requested by client.

	Test Requirement	Conclusion
1	Resilient and laminate floor coverings — Determination of indentation and	See Result
	residual indentation — Part 1: Residual indentation (ISO 24343-1:2007)	

\*\*\* FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) \*\*\*

Summer Wen

**Authorized Signatory** 



**Test Report** No.: CZHL2303001754HI Date: APR. 06, 2023 Page 2 of 3

# 1.Resilient and laminate floor coverings — Determination of indentation and residual indentation — Part 1:

## Residual indentation (ISO 24343-1:2007)

1) Number of test sample: 3 pcs

2) Sample size: 200×200mm


3) Ambient condition: (23 ± 2) °C, (50 ± 5) %RH

4) Conditioning time: 48h

Clause	Result
Determination of residual indentation	Mean value for residual indentation: 0.05mm

#### Photo Appendix

#### Photo relative to overall specimen:







Received Sample (back view)

## Result/Rating/Record Key(s)

- Result/Rating Keys: P = Pass = Meet; F = Fail = Not Meet; N/A = Not applicable = Not suitable; NR = NC = Test not conduct/requested per client request; TT = Test terminated due to the earlier failure of last test.
- II. Record Keys: "C:" means Claimed parameter; "A:" means Actual recorded from test; "D:" means Data for reference only.

# General Report Note(s)

- A. N.B. Only applicable clauses were shown.
- (1) 1mg/kg = 0.0001% (2) MDL = Method Detection Limit (3) ND = Not Detected (< MDL) B.
  - (4) "-" = Not Regulated
- C. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.
- D. This document cannot be used for publicity, without prior written approval of the SGS.





- E. Since the data and / or information above division line of front page is provided by the applicant, the relevant results or conclusions of this report are only made for these data and / or information, SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion. Testing results only apply to the sample as received.
- F. The declaration of conformity is only based on the actual value of laboratory activity, measurement uncertainty of the results not take into account.
- G. Since the above deviation of testing method is provided by the applicant, the relevant results or conclusions of this report are only made for the deviation method, SGS is not responsible for the validity of the result and /or conclusion resulted from the deviation.

\*\*\* End of Report \*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on requested or accessible at https://www.ags.com/informs.and-conditions. Attention is drawn to the limitation of liability indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects recognitions are also as the service of the company of the company. Any unauthorized alteration, foregory or fails indication of the content of pearance of this document cannot be reproduced except in full, without prior written approval of the Company, Any unauthorized alteration, foregory or fails inficient on of the posterior of pearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this text report refer only to the sample(s) tested and such assumptic(s) are related for 50 days on the company of t